

## TPU Matching Grades/Comparison:

Blue Star	BAYER	MERQUINSA	ELASTOLLAN	LUBRIZOL	SHEENTHANE	TPUCO
JT-6024				CS-686H	AS-626SH	
JT-6025	Desmocoll 540-1				AS-626SL	A-760
JT-6026	Desmocoll 540-3 Desmocoll 530-2	PEARLSTICK 45- 50/18	A-15AA9A	CS-686L	AS-626SL	
JT-6027	Desmocoll 540-4	456018		CS-686		
JT-6028	Desmocoll 540-5			CS-686	AS-626H	A-760
JT-6029		PEARLSTICK 45- 40/15		CS-686L	AS-626L	A-760
TPU resin recommended formula						
1	JT-6025: 15~30%, MEK: 15~30%, EAC: 40~70%, TOL: 20~40%					
2	JT-6029: 15%, MEK: 50~70%, EAC: 20~40%, TOL: 15~30%,					
3	JT-6026: 15%, MEK: 50~70%, EAC: 15~30%, TOL: 10~20%					
4	JT-6027 (JT-6028、JT-6024): 15%, MEK: 50~70%, EAC: 15~30%, TOL: 10~20%					