

Phenolaralkyl Resin

Name: Phenolaralkyl Resin

Specification:

<i>Appearance</i>	<i>Molecular weight (GPC)</i>	<i>Softening point (°C)</i>
	Mn: 900~1000; Mw: 1300~1500	60~70
<i>light yellow or brownish red solid</i>	Mn: 1000~1100; Mw: 1500~2000	70~80
	Mn: 1100~1200; Mw: 2000~2500	80~90

Application:

The solidifying epoxy resin with this kind of curing agent has features like low water absorbability, low expansibility under high temperature, high intensity and good heat resistance.

Package and Storage:

25kg per bag, 25kg per can. Product should avoid directly sunshine and should be kept in the clean and ventilate room in the case of room temperature. It can be kept for 6 months.